

**AMENDMENTS TO THE CLAIMS**

This listing of claims will replace all prior versions and listings of claims in the application:

**LISTING OF CLAIMS:**

1. to 12. (canceled).

13. (currently amended): A vapor phase process for producing a titanium oxide according to claim 11, comprising:

~~preliminarily heating wherein each of the a titanium halogenide-containing gas and the a oxidative gas is preliminarily heated at a temperature of at least 600°C but less than 1,100°C before being introduced~~ introducing the titanium halogenide-containing gas and the oxidative gas into the reactor

reacting the titanium halogenide-containing gas with the oxidative gas by introducing the titanium halogenide-containing gas and the oxidative gas into the reactor, to thereby allow reaction to proceed, with the temperature of the interior of the reactor being at least 800°C but less than 1,100°C, and

maintaining a residence time of the titanium halogenide-containing gas and the oxidative gas in the reactor at temperature range of at least 800°C but less than 1100°C of 0.1 seconds or less.

14. (currently amended): A process for producing a titanium oxide according to ~~claim 11~~claim 13, wherein reaction is performed by use of a raw material gas mixture containing titanium halogenide and an inert gas at a ratio of 1 : 0.1 - 20 by mol, and also by use of an oxidative gas whose amount is 1 to 30 mol on the basis of 1 mol of the titanium halogenide.

15. (currently amended): A process for producing a titanium oxide according to ~~claim 11~~claim 13, wherein the oxidative gas is an oxygen gas containing water steam.

16. (original): A process for producing a titanium oxide according to claim 15, wherein the oxidative gas contains steam in an amount of at least 0.1 mol per 1 mol of an oxygen gas.

17. (currently amended): A process for producing a titanium oxide according to ~~claim 11~~claim 13, wherein said titanium halogenide is titanium tetrachloride.

18. (currently amended): A vapor phase process for producing a titanium oxide comprising:  
reacting a titanium halogenide-containing gas with an oxidative gas by introducing the titanium halogenide-containing gas and the oxidative gas into a reactor, to thereby allow reaction to proceed, with the temperature of the interior of the reactor being at least 800°C but less than 1,100°C.

maintaining a residence time of the titanium halogenide-containing gas and the oxidative gas in the reactor at temperature range of at least 800°C but less than 1100°C of 0.1 seconds or less to obtain a titanium oxide, and

~~characterized by further~~ comprising dehalogenating the obtained titanium oxide ~~produced by the process as set forth in claim 11~~ by means of a dry dehalogenation method.

19. (original): A process for producing a titanium oxide according to claim 18, wherein, in the dry dehalogenation method, titanium oxide is heated to 200 to 500°C.

20. (original): A process for producing a titanium oxide according to claim 18, wherein, in the dry dehalogenation method, a steam-containing gas is heated to 200 to 1,000°C, and is brought into contact with titanium oxide.

21. (original): A process for producing a titanium oxide according to claim 20, wherein the steam-containing gas is air containing steam in an amount of at least 0.1 vol.%.

22. (original): A process for producing a titanium oxide according to claim 20, wherein the ratio by mass of the steam to the titanium oxide is at least 0.01.

23. (currently amended): A vapor phase process for producing a titanium oxide comprising:

reacting a titanium halogenide-containing gas with an oxidative gas by introducing the titanium halogenide-containing gas and the oxidative gas into a reactor, to thereby allow reaction to proceed, with the temperature of the interior of the reactor being at least 800°C but less than 1,100°C,

maintaining a residence time of the titanium halogenide-containing gas and the oxidative gas in the reactor at temperature range of at least 800°C but less than 1100°C of 0.1 seconds or less to obtain a titanium oxide, and

~~characterized by further comprising dehalogenating the obtained titanium oxide produced by the method as set forth in claim 11~~ by means of a wet dechlorination method, to thereby yield a slurry containing a titanium oxide.

24. (original): A process for producing a titanium oxide according to claim 23, wherein, in the wet dehalogenation method, titanium oxide is suspended in water, and chlorine which is transferred to a liquid phase is discharged to the outside of the resultant suspension.

25. (original): A process for producing a titanium oxide according to claim 23 or 24, wherein, in the wet dehalogenation method, separation of chlorine is performed by use of an ultrafiltration membrane.

26. (original): A process for producing a titanium oxide according to claim 23 or 24, wherein, in the wet dehalogenation method, separation of chlorine is performed by use of a reverse osmosis membrane.

27. (original): A process for producing a titanium oxide according to claim 23 or 24, wherein, in the wet dechlorination method, separation of chloride is performed by use of a filter press.

28. to 36. (canceled).